



## VHM-8-Fachwerkzeuge 60° Solid carbide 8-fold tools 60°



Artikelnummer Article-No.	d1	l1	l2	d2 h6
E.5616.0.0050	0.5	39	1	3,0
E.5616.0.0200	2	39	4	3,0
E.5616.0.0250	2.5	39	5	3,0
E.5616.0.0300	3	50	6	4,0
E.5616.0.0400	4	50	8	5,0
E.5616.0.0500	5	57	10	6,0
E.5616.0.0600	6	57	12	6,0
E.5616.0.0800	8	72	16	10,0
E.5616.0.1000	10	83	18	12,0
E.5616.0.1200	12	83	20	12,0
E.5616.0.1600	16	92	26	16,0



Individuelle Schnittdaten online im  
Schnittdaten-Rechner berechnen lassen:  
Calculate individual cutting  
data online in the cutting data calculator  
[www.nachreiner-schnittdaten.eu](http://www.nachreiner-schnittdaten.eu)

Materialbezeichnung material description	Bearbeitung Process	Vc m/min	fz						
			∅ 0.50-3.00	∅ 4.00-5.00	∅ 6.00	∅ 8.00	∅ 10.00	∅ 12.00	∅ 16.00
PA allg. Stähle General steels	Reibahlen und Senker VHM	120.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	105.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	90.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	80.00	0.070	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	65.00	0.005	0.010	0.018	0.022	0.030	0.045	0.060
PV Vergütungsstähle < 850N/mm <sup>2</sup> Tempering steel < 850N/mm <sup>2</sup>	Reibahlen und Senker VHM	90.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	80.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Reibahlen und Senker VHM	65.00	0.005	0.010	0.018	0.022	0.030	0.045	0.060
M Rost und säurebeständige Stähle Stainless steels	Reibahlen und Senker VHM	50.00	0.005	0.010	0.018	0.022	0.030	0.045	0.060
	Reibahlen und Senker VHM	80.00	0.005	0.010	0.018	0.022	0.030	0.045	0.060
M Rost und säurebeständige Stähle >700N/mm <sup>2</sup> Stainless steels >700N/mm <sup>2</sup>	Reibahlen und Senker VHM	60.00	0.005	0.010	0.018	0.022	0.030	0.045	0.060

# PRODUCT DATA SHEET



Materialbezeichnung material description	Bearbeitung Process	Vc m/min	fz						
			∅ 0.50-3.00	∅ 4.00-5.00	∅ 6.00	∅ 8.00	∅ 10.00	∅ 12.00	∅ 16.00
K Gusseisen Cast iron	Reibahlen und Senker VHM	120.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Temperguss Malleable cast iron	60.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Gusseisen mit Kugelgraphit Nodular cast iron	90.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
N AL- und AL-Legierungen AL und AL-alloys	Reibahlen und Senker VHM	300.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	AL- und AL-Legierungen AL und AL-alloys	250.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080
	Kupfer, Messing, Bronze, Rotguss Copper, brass, bronze, red brass	200.00	0.007	0.015	0.025	0.032	0.045	0.065	0.080