

VHM-Entgrater 90°, WN, gedraht, Solid carbide deburring tool 90°, company std. twisted



P	P	M	K	N	S	H
●	●	●	●	●		

Artikelnummer Article-No.	flutes	d1 h6	l1	d2
E.5642.1.0300	3	3	39	3,0
E.5642.1.0400	3	4	50	4,0
E.5642.1.0600	5	6	57	6,0
E.5642.1.0800	5	8	63	8,0
E.5642.1.1000	5	10	72	10,0
E.5642.1.1200	6	12	83	12,0
E.5642.1.1600	6	16	92	16,0



Individuelle Schnittdaten online im
Schnittdaten-Rechner berechnen lassen:
Calculate individual cutting
data online in the cutting data calculator
www.nachreiner-schnittdaten.eu

Materialbezeichnung material description	Bearbeitung Process	Vc m/min	fz							
			Ø 0.013	Ø 0.018	Ø 0.036	Ø 0.048	Ø 0.060	Ø 0.080	Ø 0.100	
PA allg. Stähle General steels	Reibahlen und Senker VHM	190.00	0.013	0.018	0.036	0.048	0.060	0.080	0.100	
	Reibahlen und Senker VHM	170.00	0.013	0.018	0.036	0.048	0.060	0.080	0.100	
	Reibahlen und Senker VHM	160.00	0.012	0.016	0.023	0.038	0.044	0.050	0.075	
	Reibahlen und Senker VHM	140.00	0.012	0.016	0.023	0.038	0.440	0.050	0.075	
	Reibahlen und Senker VHM	120.00	0.012	0.016	0.023	0.038	0.044	0.050	0.075	
PV Vergütungsstähle < 850N/mm² Tempering steel < 850N/mm²	Reibahlen und Senker VHM	160.00	0.012	0.016	0.023	0.038	0.440	0.050	0.075	
	Reibahlen und Senker VHM	140.00	0.012	0.016	0.023	0.038	0.044	0.050	0.075	
	Reibahlen und Senker VHM	120.00	0.012	0.016	0.023	0.038	0.044	0.050	0.075	
	Reibahlen und Senker VHM	100.00	0.012	0.016	0.023	0.038	0.044	0.050	0.075	
M Rost und säurebeständige Stähle Stainless steels	Reibahlen und Senker VHM	110.00	0.009	0.013	0.025	0.034	0.050	0.070		
	Reibahlen und Senker VHM	75.00	0.006	0.009	0.019	0.025	0.040	0.060		
K Gusseisen Cast iron	Reibahlen und Senker VHM	150.00	0.012	0.017	0.033	0.044	0.060	0.070	0.090	
	Reibahlen und Senker VHM	80.00	0.012	0.017	0.033	0.044	0.060	0.070	0.090	
	Reibahlen und Senker VHM	100.00	0.012	0.017	0.033	0.044	0.060	0.070	0.090	

PRODUCT DATA SHEET



Materialbezeichnung material description		Bearbeitung Process	Vc m/min	fz						
				Ø 0.013	Ø 0.018	Ø 0.036	Ø 0.048	Ø 0.060	Ø 0.080	Ø 0.100
N	AL- und AL-Legierungen AL und AL-alloys	Reibahlen und Senker VHM	300.00	0.017	0.023	0.047	0.062	0.080	0.100	0.130
	AL- und AL-Legierungen AL und AL-alloys	Reibahlen und Senker VHM	250.00	0.017	0.023	0.047	0.062	0.080	0.100	0.130
	AL- und AL-Legierungen >12% Si AL und AL-alloys >12% Si	Reibahlen und Senker VHM	200.00	0.017	0.023	0.047	0.062	0.080	0.100	0.130
	Kupfer, Messing, Bronze, Rotguss Copper, brass, bronze, red brass	Reibahlen und Senker VHM	180.00	0.017	0.023	0.047	0.062	0.080	0.100	0.130